



## DATA SHEET

### Filter media

Ultra-Web® on Spunbond

### Ultra-Web® on Spunbond

<b>Appearance</b>	White, corrugated
<b>Use</b>	Pleatable filter media
<b>Composition</b>	Spunbond polyester with nanofiber layer
<b>Area weight</b>	260 g/m <sup>2</sup>
<b>Thickness</b>	0.61 mm
<b>Air Permeability (Frazier)</b>	340 m <sup>3</sup> /m <sup>2</sup> .h at 125 Pa
<b>IFA/BIA certificate</b> (DIN 660335-2-69)	Class M Test report number: 201523949/6210
<b>Temperature (dry heat)</b>	
Continuous	93 °C
Peaks	110 °C
<b>Chemical resistance</b>	
Hydrolysis	N/A
Acids	Good
Alkalis	Good
Oxidising agents	Good
Organic solvents	Good
<b>Abrasion resistance</b>	Excellent
<b>Supports combustion</b>	Yes
<b>Application field</b>	<p>Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food and industrial processing, when product contamination must be minimised. Excellent performance on moist, hygroscopic or agglomerative dust. High filtration efficiency on very fine particulate &lt; 1 micron.</p> <p>Chemical processing, food processing, general industrial.</p>