



## DATA SHEET

**Filter media**  
Standard Polyester

### Standard Polyester

<b>Appearance</b>	White, uncorrugated
<b>Use</b>	Pleatable filter media
<b>Composition</b>	Spunbond polyester
<b>Area weight</b>	250 g/m <sup>2</sup>
<b>Thickness</b>	0.57 mm
<b>Air Permeability</b> (DIN 29073)	470 m <sup>3</sup> /m <sup>2</sup> .h at 200 Pa
<b>IFA/BIA certificate</b> (DIN 660335-2-69)	N/A
<b>Temperature (dry heat)</b>	
Continuous	93 °C
Peaks	110 °C
<b>Chemical resistance</b>	
Hydrolysis	N/A
Acids	Good
Alkalis	Good
Oxidising agents	Good
Organic solvents	Good
<b>Abrasion resistance</b>	Excellent
<b>Supports combustion</b>	Yes
<b>Application field</b>	Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food, and industrial processing when product contamination must be minimised. Excellent performance on moist, hygroscopic or agglomerative dust.